



DURAT® SOLID SURFACE MATERIAL TECHNICAL PROPERTIES

MECHANICAL AND PHYSICAL PROPERTIES

PROPERTY	METHOD	RESULT
APPROXIMATE WEIGHT (12mm THICK DURAT)		18.3 kg / m ²
DENSITY	ASTM D792A	1,41 ± 0,01 g/cm ³
FLEXURAL STRENGTH	ASTM D 790	36,3 ± 2,6 MPa
MODULUS OF ELASTICITY (FLEXURAL)	ASTM D 790	4810 ± 50 MPa
TENSILE STRENGTH	ASTM D 638	16,1 ± 3,1 MPa
MODULUS OF ELASTICITY (TENSILE)	ASTM D 638	4780 ± 260 MPa
ELONGATION AT BREAK	ASTM D 638	0,3 ± 0,1 %
IMPACT RESISTANCE(CHARPY)	ISO 179	1,7 ± 0,5 KJ /m ²
BARCOL HARDNESS	ASTM D2583	46 ± 2
LINEAR THERMAL EXPANSION (COEFFICIENT)	ASTM D 696	72 x 10 ⁻⁶ (0,0072 % / °C)

FIRE TESTS - REACTION TO FIRE, IGNITABILITY OF BUILDING MATERIALS

TEST	RESULT
ISO 5657-1986E (NT FIRE 033)	CLASS 1
BS 476: Part 7: 1997	CLASS 1

EMISSION CLASSIFICATION OF BUILDING MATERIALS

THE BUILDING FOUNDATION RTS	CLASS M1
-----------------------------	----------

SUITABILITY FOR SURFACES WHERE FOODSTUFFS ARE HANDLED

VTT BIOTECHNOLOGY AND FOOD RESEARCH / RESEARCH REPORT NO. BEL71/98
--



RESISTANCE TO CHEMICALS

EVERYDAY HOUSEHOLD SUBSTANCES

BLACK CRAYON	1	HAIR DYE	1
BLACK SHOE POLISH	1	IODINE SOLUTION	1
BLUE INK (BALL POINT)	4	LIPSTICK	1
BLUE INK (WASHABLE)	1	PLAIN MUSTARD	2
COFFEE	1	TEA	1
ETHANOL 48%	1	TOMATO KETCHUP	1
GENTIAN VIOLET SOLUTION	1	VEGETABLE OIL	1
GRAPE JUICE	1	WHOLE MILK	1

1 = NON-STAINING

2 = REMOVABLE BY ALCOHOL OR NAPHTHA

3 = REMOVABLE BY 1ST APPLICATION OF HOUSEHOLD SCOURING POWDER

4 = REMOVABLE BY 2ND APPLICATION OF HOUSEHOLD SCOURING POWDER

5 =

CHEMICALS - SERVICEABLE AND REPAIRABLE

THE SURFACE FINISH SHALL BE UNAFFECTED BY THE REAGENTS EXCEPT FOR SUPERFICIAL SURFACE CHANGES WHICH ARE REMOVABLE BY 600 GRIT WET SANDPAPER. ANY RESULTING DAMAGE SHOULD NOT IMPAIR USE OF UNIT AND SHOULD BE EASILY REPAIRABLE USING ABRASIVE AND POLISHING COMPOUNDS.

ACETONE

AMMONIA, 10 % IN H₂O

AMYL ACETATE

CITRIC ACID, 10 % IN H₂O

ETHYL ACETATE

ETHYL ALCOHOL

HYDROGEN PEROXIDE, 3 % IN H₂O

LYE, 1-2 % (DRAIN CLEANER)

NAPHTHA

PINE OIL

PHENOL, 5 % (DISINFECTANT)

SODIUM HYPOCHLORITE (BLEACH)

TOLUENE

UREA, 6,0 % IN H₂O

VINEGAR



DURAT® FINISH PERFORMANCE
BRITISH STANDARDS TESTING AND EVALUATION
 TEST PIECE: DURAT® 910 DATE 08/2007

TEST	RESULTS	COMMENT
MECHANICAL DAMAGE		
BS3962 PT.6. SCRAPE S.P.	5	20 NEWTONS
SCRAPE P.S.	5	28+ NEWTONS
WET HEATS BS EN 12721		
55° C	5	NO DAMAGE
70 ° C	5	NO DAMAGE
85° C	5	NO DAMAGE
DRY HEATS BS EN 12722		
120° C	4	SLIGHT MARKING
140 ° C	3	SLIGHT VISIBLE DISTURBANCE
160 ° C	2	VISIBLE DISTURBANCE
COLD LIQUIDS BS EN 12720		
ACETONE	2	VISIBLE DISTURBANCE
ETHANOL 96%	4	SLIGHT MARKING
ETHANOL 48%	5	NO DAMAGE
TEA	5	NO DAMAGE
COFFEE	5	NO DAMAGE
DISINFECTED PHENOL	3	CHANGE OF GLOSS LEVEL
DISINFECTED CHLORO	5	NO DAMAGE
PARAFFIN OIL	5	NO DAMAGE
BLACKCURRANT JUICE	5	NO DAMAGE
AMMONIA SOLUTION	5	NO DAMAGE
ACETIC ACID	5	NO DAMAGE
OLIVE OIL	5	NO DAMAGE
COLD OILS (24HRS)	5	NO DAMAGE
COLD FATS (24HRS)	5	NO DAMAGE
LARGE BALL IMPACT BS6222/3 CLAUSE 7.2.1		
10 MM MAX 4 4 MM	4	4 MM

Notes:

- 1) The rating code for the results of the tests are explained in the various relevant British Standards. A rating of 5 is the best result that can be achieved and a rating of 1 is the poorest.
- 2) Any test given a 1 rating automatically fails the test specimen