

Technical Specifications

TEST PERFORMED	ASTM	RESULTS
Static coefficient of friction	C - 1028	Dry: 0.73 Wet: 0.68
Modulus of rupture	C - 120	Dry: 1,800 psi Wet: 800 psi
Modulus of elasticity	C - 469	1,75 x 10 ⁶ psi
Shear strength	D - 732	Dry: 1,200 psi Wet: 1,170 psi
Tensile strength	D - 209	Dry: 600 psi Wet: 450 psi
Compressive strength	C - 170	Dry: 3,900 psi Wet: 3,000 psi
Water vapor permeance	E - 96	6.5perms
Thermal conductivity (k)	C - 58	1.43 BTU-In/Hr F
Flame spread and smoke development index	E - 84	Flame: 0 index Smoke: 0 index