

Technical Specifications

TEST PERFORMED	ASTM	RESULTS
Coefficient of friction	C - 1028	Dry: 0.64; Wet: 0.61 (Polished) Dry: 0.71; Wet: 0.68 (Honed) Dry: 0.74; Wet: 0.70 (Sandblasted)
Resistance to fire		Class 0
Freeze - thaw	C - 666	None (300 cycles)
Compressive strength	D - 170	14,000 - 24,000 psi
Modulus of rupture	C - 99	1,550 psi
Flexural strength	C - 880	1,973 psi
Water absorption	C - 97	3.2%