


TECHNICAL SPECIFICATIONS

CHARACTERISTIC	TEST METHODS	SPECIFICATION
Width	ISO 10545-2	1400 mm
Length	ISO 10545-2	3200 mm
Thickness	ISO 10545-2	20.0 ± 0.5 mm
Water absorption	ISO 10545-3	≤ 0.50 %
Breaking strength	ISO 10545-4	Not less than 3000 N
Resistance to deep abrasion	ISO 10545-6	Maximum 175 mm ³
Frost resistance	ISO 10545-12	Resisted
Resistance to thermal shock	ISO 10545-9	Resisted
Resistance to stains	ISO 10545-14	Minimum Class 4*
Resistance to chemical - Common household - Acid	ASTM C650	Not damaged
Reaction to fire	EN 13501-1	Class A1**



* Based on ISO 10545-14, Class 4 is defined that the stain is removed using a weak commercial cleaning agent.

** Based on EN 13501-1, Class A1 is defined as non-combustible product.

Remark: Specific test result by lot can be obtained upon request.



Contact
SCG Cement-Building Materials Co.,Ltd.
1 Siam Cement Rd., Bangsue,
Bangkok 10800, Thailand

www.geoluxe.com | info@geoluxe.com

GEOLUXE